



CHAORYAN

PRODUCT DATA SHEET

Luoyang Naibao New Materials Co., Ltd.

Brown Fused Alumina F14

Grade / size: F14 | Product family: F Grit

Document ID: CY-PDS-EN-2280 | Version: 1.0 | Date: 2026-10-02

Product overview

Brown Fused Alumina F14 is a CHAORYAN f grit product for bonded abrasives, blasting and industrial grinding. Confirm the grade, chemistry, particle size distribution and packing in the agreed technical specification.

Specifications

Product	Brown Fused Alumina F14
Grade / size	F14
Product family	F Grit
Packing	Confirm bag or bulk packing and labeling with the order.

Chemical composition

Parameter	A	A-B
Al ₂ O ₃ (%)	95.00–97.50	≥93.00
TiO ₂ (%)	1.50–3.80	1.50–4.20
CaO (%)	≤0.45	—

Physical properties

Parameter	A	A-B
Magnetic content ≤ (%)	0.0460	0.0740
Calcination temperature (°C), A grade	1050–1350	—

Particle size distribution

Distribution limits and sieve fractions are confirmed in the agreed technical specification and batch test report.

Applications

Bonded abrasives, blasting and industrial grinding.

Processing and packing

Discuss particle shape, grading and sample matching for the intended process.

Confirm bag or bulk packing and labeling with the order.

Specific guaranteed values follow the agreed technical specification and batch test result.

CONTACT

lychaoyan@gmail.com

<https://en.jingangshan.cn>

<https://en.jingangshan.cn/products/brown-fused-alumina-f14/>

